



MULTICLEAR®

Box 2Wall HG

MULTICLEAR® Box 2Wall HG is a range of extruded multiwall polycarbonate sheets specifically designed to offer increased transparency combined with solid rigidity. This results in cost savings by reducing the number of glazing bars required, thereby increasing light transmission.

MULTICLEAR® Box 2Wall HG is a transparent and translucent sheet with One-sided UV protection (also available with two sides UV protection). Available in thickness 16 mm only. Standard production is available in clear, opal and bronze. Other colours are available on request.

MULTICLEAR® Box 2Wall HG has a 10-year limited warranty against discolouration, loss of impact strength and light transmission due to weathering. Manufactured under controlled production conditions to ensure consistent product quality.

Fire performance:

Classified B-s1, d0 according to EN 13501-1. The material is suitable for applications where reaction to fire classification is required.

ALSO AVAILABLE:

MULTICLEAR® HAMMER FINISH
 MULTICLEAR® SOLAR CONTROL
 MULTICLEAR® RPC

MULTICLEAR® Box 2Wall HG BENEFITS:

- Less structural glazing bars hence increased light transmission
- Large rib distance offering greater transparency
- Good wind and snow loading capacity
- Aesthetic glazing

APPLICATION AREAS:

Building industry – roofing, cladding, sidewalls, conservatories, domes, skylights, sheds, car ports, smoke vents, swimming pool covers, suspended ceilings, glasshouses, shopping center roofing, railway/metro station, stadia roofing and partitions.

Agriculture – greenhouses, lorry/tractor ports and farm/barn buildings.

Packaging – boxes for lamp optics, neon signs, pallet shields and protective covers for fragile items.

Advertising – illuminated signs and panels.

MULTICLEAR® Box 2Wall HG – technical specification

Multiclear® Box 2Wall HG	Thickness [mm]	Rib distance [mm]	Mass per unit area [g/m ²]	U-value [W/(m ² ·K)]	Standard Width [mm]	UV protection	Standard colours
	16	31	3400 – 3600	2.8	1200 / 980	1-sided (2-sided optional)	Clear / Opal / Bronze

U-values calculated according to EN 673 (vertical heat flow).

Polycarbonate material properties:

Property	Value	Unit	Standard
Physical properties			
Density	1,2	g/cm ³	ISO 1183
Refractive index (20 °C)	1,586		ISO 489
Moisture absorption 24 h, 23 °C, 50% RH	0,15	%	ISO 62
Mechanical properties			
Tensile strength at yield (at break)	63 (70)	N/mm ²	ISO 527
Elongation at yield (at break)	6 (110)	%	ISO 527
Elastic modulus	>2300	N/mm ²	ISO 527
Flexural modulus	>2300	N/mm ²	ISO 178
Charpy unnotched impact strength -40 °C	NB	kJ/m ²	ISO 179/1eU
Charpy notched impact strength -30 °C	11	kJ/m ²	ISO 179/1eA
Izod notched impact strength +23 °C	65	kJ/m ²	ISO 180/1A
Izod notched impact strength -30 °C	10	kJ/m ²	ISO 180/1A
Thermal properties			
Coefficient of linear thermal expansion (20–70 °C)	65x10 ⁻⁶	K ⁻¹	ISO 11359-2
Heat deflection temperature, HDT A (1,80 N/mm ²)	132	°C	ISO 75
Heat deflection temperature, HDT B (0,45 N/mm ²)	142	°C	ISO 75
Vicat temperature VST/B 120	149	°C	ISO 306
Vicat temperature VST/B 50	148	°C	ISO 306
Thermal conductivity	0,20	W/m·K	ISO 8302

Properties reported here are typical values for polycarbonate. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.