



MAKROCLEAR™

MAKROCLEAR™ is transparent polycarbonate sheet. The product is produced with vast knowledge of our production team experienced in producing mono, co and tri-extrusion. The product is virtually unbreakable with extremely high impact resistance and offers high temperature performance too.

MAKROCLEAR™ provides designers, specifiers and architects with possibilities to use transparent polycarbonate sheets in applications where high clarity and optical performance is required. The consistent high quality demands from the market helps to improve machining, screen printability and thermoformability

EXCELLENT FIRE PERFORMANCE complying requirements to EN 13501-1 (EUROPEAN BUILDING STD). In case of fire, the sheet will melt and allow venting where heat and smoke will be let out and therefore reduce the growth of fire by flame spread.

MAKROCLEAR™ BENEFITS:

- Good optical quality
- Half the weight of glass
- More than 10 times the impact strength of high impact PMMA
- Easy to thermoform or fabricate
- Good fire classification

APPLICATION AREAS:

MAKROCLEAR™ is the perfect solution for machining protection, safety glazing, ice hockey rinks, vandal protection etc. MAKROCLEAR™ thermoforms very easily and is often used in signs, displays, riot shields, windows, medical equipment, bicycle helmets etc.

DELIVERY PROGRAM:

Standard size: 2050 x 3050 mm

2050 x 3050 mm (2 – 20 mm)

Thickness range: 0,8 – 20 mm

Colour: Clear

Embossing: ICE™, TEX™, Grain 35, ANTI-REFLEX™

Special sizes and thicknesses on request

MAKROCLEAR™ TECHNICAL SPECIFICATIONS

| Property | Value | Unit | Standard |
|--|---------------------|-------------------|-------------|
| Physical properties | | | |
| Density | 1,2 | g/cm ³ | ISO 1183 |
| Refractive index (20 °C) | 1,586 | | ISO 489 |
| Moisture absorption 24 hours, 23 °C, 50% RH | 0,15 | % | ISO 62 |
| Mechanical properties | | | |
| Tensile strength at yield (at break) | 60 (70) | N/mm ² | ISO 527 |
| Elongation at yield (at break) | 6 (110) | % | ISO 527 |
| Elastic modulus | >2300 | N/mm ² | ISO 527 |
| Flexural modulus | >2300 | N/mm ² | ISO 178 |
| Charpy unnotched impact strength -40 °C | NB | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength -30 °C | 11 | kJ/m ² | ISO 179/1eA |
| Izod notched impact strength +23 °C | 65 | kJ/m ² | ISO 180/1A |
| Izod notched impact strength -30 °C | 10 | kJ/m ² | ISO 180/1A |
| Thermal properties | | | |
| Linear coefficient of thermal expansion (20-70 °C) | 65x10 ⁻⁶ | K ⁻¹ | ISO 11359-2 |
| Heat deflection temperature, HDT A (1,80 N/mm ²) | 132 | °C | ISO 75 |
| Heat deflection temperature, HDT B (0,45 N/mm ²) | 142 | °C | ISO 75 |
| Vicat temperature VST/B 120 | 149 | °C | ISO 306 |
| Vicat temperature VST/B 50 | 148 | °C | ISO 306 |
| Thermal conductivity | 0,20 | W/m.K | DIN 8302 |
| Electrical properties | | | |
| Volume resistivity, dry | >10 ¹⁴ | Ω . m | IEC 60093 |
| Surface resistivity, dry | 10 ¹⁶ | Ω | IEC 60093 |
| Dielectric strength, dry | 30 | kV/mm | IEC 60243 |
| Dielectric constant, dry 50 Hz | 3 | | IEC 60250 |
| Dielectric constant, dry 1 MHz | 2,9 | | IEC 60250 |
| Dissipation factor (tan δ), dry 50 Hz | 0,001 | | IEC 60250 |
| Dissipation factor (tan δ), dry 1 MHz | 0,01 | | IEC 60250 |

Properties reported here are typical values. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.