

SAPHIR® AF

SAPHIR® is our range of polycarbonate coated sheet.

SAPHIR® AF is an anti-fog coated polycarbonate sheet. The high impact strength of polycarbonate is combined with effective protection against water vapor condensation and clear visibility for numerous applications.

SAPHIR® AF weighs about half of standard glass, yet the product is virtually unbreakable.

ALSO AVAILABLE:

2-side AF coating, 1-side AF coating, 1-side scratch resistant coating /1-side AF coating, any colour or tint.

SAPHIR® AF BENEFITS:

- Protection against water vapor condensation
- High optical quality and outstanding clarity
- Impact Resistant
- More than 10 times the impact strength of high impact PMMA

APPLICATION AREAS:

Applications where protection against water vapor condensation is needed such as visors for motorcycle, industrial visors and googles, police helmet visors and multiple other applications.

DELIVERY PROGRAM:

Standard size: 2000 x 3000 mm

(<2 mm: 1250x2000 mm)

Thickness range: 1 – 6 mm

1 side or 2 sides coated

Special sizes and thicknesses on request

SAPHIR® AF TYPICAL PROPERTY VALUES

| Property | Value | Unit | Standard |
|--|---------------------|-------------------|-------------------------|
| Physical properties | | | |
| Density | 1,2 | g/cm ³ | ISO 1183 |
| Refractive index (20 °C) | 1,586 | | ISO 489 |
| Moisture absorption 24 h, 23 °C, 50% RH | 0,15 | % | ISO 62 |
| Mechanical properties | | | |
| Tensile strength at yield (at break) | 60 (70) | N/mm ² | ISO 527 |
| Elongation at yield (at break) | 6 (110) | % | ISO 527 |
| Elastic modulus | >2300 | N/mm² | ISO 527 |
| Flexural modulus | >2300 | N/mm² | ISO 178 |
| Charpy unnotched impact strength -40 °C | NB | kJ/m² | ISO 179/1eU |
| Charpy notched impact strength -30 °C | 11 | kJ/m² | ISO 179/1eA |
| Izod notched impact strength +23 °C | 65 | kJ/m² | ISO 180/1A |
| Izod notched impact strength -30 °C | 10 | kJ/m² | ISO 180/1A |
| Thermal properties | | | |
| Coefficient of linear thermal expansion (20-70 °C) | 65x10 ⁻⁶ | K ⁻¹ | ISO 11359-2 |
| Thermal conductivity | 0,20 | W/m.K | ISO 8302 |
| Coating properties | | | |
| Adhesion | GT-0 | | DIN 53151 / ISO 2409 |
| Taber Abrasion**, CS 10F, 500g, 100 cycles | <10 | % Haze | ASTM D1044 |
| Anti-fog effect*** | >60 | Sec | Internal test method |

^{*}Based on raw material data

Properties reported here are typical values for polycarbonate. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.



^{**}Taberhaze: Taber abrader, 500g load, CS 10F wheels, 100 cycles

^{***}Anti-fog effect: Fogging time over water bath with 50°C water temperature.