



POLYCARBONATE OPAQUE ATECH 7100

POLYCARBONATE OPAQUE ATECH 7100 is coloured opaque polycarbonate sheet. The product is produced with vast knowledge of our production team experienced in producing mono, co and tri-extrusion. The product is virtually unbreakable with extremely high impact resistance. The product offers high temperature performance.

POLYCARBONATE OPAQUE ATECH 7100 provides designers, specifiers and architects with possibilities to use opaque polycarbonate sheets in applications where matt surface adds value and also provides the classy look.

RECYCLING

Our total recycling concept (TRC), is a major advantage in today's environmentally friendly market. The TRC concept covers all types of sheets to provide you with cost saving. Off-cuts from the sheets can be used in production of new sheets by co-extruding virgin material as the top layer. Care is taken that all quality requirements are met.

POLYCARBONATE OPAQUE ATECH 7100

BENEFITS:

- High impact strength
- Usable over a wide temperature range
- Easy to thermoform

APPLICATION AREAS:

Outdoor for automotive, signage, advertising, street furniture, building and construction, safety and security, point of sale/purchase, cladding and decoration, protection etc.

DELIVERY PROGRAM:

Standard size: 1250 x 2050 mm

Max width: 1700 mm

Thickness range: 1,5 – 8 mm, other upon request

Colours: Customer specific

Embossing: 00/35, other upon request

POLYCARBONATE OPAQUE ATECH 7100 TYPICAL PROPERTY VALUES

Property	Value	Unit	Standard
Physical properties			
Density	1,20	g/cm ³	ISO 1183
Mechanical properties			
Tensile strength at yield	60	N/mm ²	ISO 527-2
Tensile elongation at yield	6	%	ISO 527-2
Tensile strength at break	45	N/mm ²	ISO 527-2
Tensile elongation at break	>50	%	ISO 527-2
Elastic modulus	2200	N/mm ²	ISO 527-2
Flexural modulus*	2300	N/mm ²	ISO 178
Izod notched impact strength +23°C	65	kJ/m ²	ISO 180/A
Izod notched impact strength -23°C	12	kJ/m ²	ISO 180/A
Izod notched impact strength -30°C	11	kJ/m ²	ISO 180/A
Charpy notched impact strength +23°C	60	kJ/m ²	ISO 179-1/1eA
Charpy notched impact strength -23°C	12	kJ/m ²	ISO 179-1/1eA
Charpy notched impact strength -30°C	11	kJ/m ²	ISO 179-1/1eA
Rockwell hardness*	M70	R-scale	ISO 2039-2
Thermal properties			
Vicat temperature VST/B120 (0,45 N/mm ²)	140	°C	ISO 306
Heat deflection temperature HDT A (1,80 N/mm ²)	135	°C	ISO 75-2
Fire properties			
Flammability 1,6 mm*	HB	Class	UL 94

* Value based on information given from resin supplier.

Properties reported here are typical values. Arla Plast makes no representation that the material in any particular shipment will conform exactly to the values given. The above information is based upon experience and given in good faith. Due to many factors which are outside our knowledge and control, no warranty is given or is to be implied with respect to such information. Detailed product specification and technical manual/information is available on request.